

Application No.: 09/760,169  
Filing Date: January 12, 2001  
Page: 2

**AMENDMENTS TO THE CLAIMS:**

This listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1. (Currently Amended) A transparent, low-flammability, UV-resistant, biaxially oriented film made from a film forming thermoplastic and having a thickness of from 5 to 300  $\mu\text{m}$ , wherein the film comprises:

crystallizable thermoplastic as the principal constituent ;  
at least one UV stabilizer;  
at least one flame retardant,

where the UV stabilizer is thermally stable at temperatures exceeding 240 °C, said oriented film has a luminous transmittance of >80% when measured according to ASTM D 1003; a surface gloss of >100 when measured at an angle of 20° according to DIN 67530; a haze of  $\leq 20\%$  when measured according to ASTM S 1003 and a yellowness index of  $\leq 10$  as measured in accordance with DIN 6167,

wherein said film comprises flame retardant consisting of one or more organic phosphorous compounds and

said film exhibits a longitudinal modulus of elasticity of greater than 3200 N/mm<sup>2</sup> after said film has been heat treated for 100 hours at 100 °C and

said crystallizable thermoplastic ~~is selected from the group consisting~~ consists of polyethylene terephthalate , or polybutylene terephthalate or mixtures thereof.

2. (Canceled)

Application No.: 09/760,169  
Filing Date: January 12, 2001  
Page: 3

3. (Original) The film as claimed in claim 1, which has one or more layers and has additionally been coated with copolyesters or with adhesion promoters.

4. (Original) The film as claimed in claim 1, wherein the amount of flame retardant present is from 0.5 to 30% by weight, based on the weight of the layer of the crystallizable thermoplastic.

5. (Original) The film as claimed in claim 1, wherein the amount of the UV stabilizer present is from 0.01 to 5% by weight, based on the weight of the layer of the crystallizable thermoplastic.

6. (Original) The film as claimed in claim 1, wherein the UV stabilizer present comprises light stabilizers selected from one or more elements of the group consisting of 2-hydroxybenzophenones, 2-hydroxybenzotriazoles, organonickel compounds, salicylic esters, cinnamic ester derivatives, resorcinol monobenzoates, oxanilides, hydroxybenzoic esters, sterically hindered amines and triazines.

7. (Canceled)

8. (Previously Presented) The film as claimed in claim 1, wherein the flame retardant is dimethyl methylphosphonate.

9. (Previously Presented) The film as claimed in claim 1, wherein from 0.1 to 1.0% by weight of a hydrolysis stabilizer selected from the group consisting of alkali metal stearates, alkaline earth metal stearates, alkali metal carbonates and alkaline earth metal carbonates, or from 0.05 to 0.6% by weight, of a hydrolysis stabilizer selected from one or more elements of the group consisting of phenolic stabilizers having a molar mass above 500 g/mol is additionally present in the film.

Application No.: 09/760,169  
Filing Date: January 12, 2001  
Page: 4

10. (Previously Presented) The film as claimed in claim 9, wherein the hydrolysis stabilizer is a phenolic stabilizer selected from pentaerythrityl tetrakis-3-(3,5-di-tert-butyl-4-hydroxyphenyl)propanoate or 1,3,5-trimethyl-2,4,6-tris(3,5-di-tert-butyl-4-hydroxybenzyl)benzene.

11. (Canceled)

12. (Canceled)

13. (Canceled)

14. (Canceled)

15. (Canceled)

16. (Canceled)

17. (Canceled)

18. (Canceled)

19. (Currently Amended) A transparent, low-flammability, UV-resistant, biaxially oriented film made from a film forming thermoplastic and having a thickness of from 5 to 300  $\mu\text{m}$ , wherein the film comprises:

~~at least one~~ crystallizable thermoplastic consisting of polyethylene terephthalate, polybutylene terephthalate or mixtures thereof;

at least one UV stabilizer selected from the group consisting of  
2-hydroxybenzophenones, 2-hydroxybenzotriazoles and triazines;  
and  
flame retardant;

Application No.: 09/760,169  
Filing Date: January 12, 2001  
Page: 5

wherein the UV stabilizer is thermally stable at temperatures exceeding 240 °C,  
and said film comprises flame retardant consisting of one or more organic  
phosphorous compounds and

said film exhibits a longitudinal modulus of elasticity of greater than 3200 N/mm<sup>2</sup>  
after said film has been heat treated for 100 hours at 100 °C.

20. (Currently Amended) A transparent, low-flammability, UV-resistant, biaxially  
oriented film made from a film forming thermoplastic and having a thickness of from 5  
to 300 µm, wherein the film comprises:

at least one crystallizable thermoplastic consisting of polyethylene  
terephthalate, polybutylene terephthalate or mixtures thereof;

at least one UV stabilizer and  
flame retardant;

wherein the UV stabilizer is thermally stable at temperatures exceeding 240 °C,  
said film satisfying the requirements of UL class 94 VTM-0, and said film comprises  
flame retardant consisting of one or more organic phosphorous compounds and

said film exhibits a longitudinal modulus of elasticity of greater than 3200 N/mm<sup>2</sup>  
after said film has been heat treated for 100 hours at 100 °C.

21. (Currently Amended) A transparent, low-flammability, UV-resistant, multi-  
layered biaxially oriented film having a thickness of 5 to 300 µm, said film comprising a  
base layer disposed between two outer layers, said film further comprising

- (i) crystallizable thermoplastic,
- (ii) UV stabilizer in said outer layers alone and
- (iii) flame retardant in said base layer alone,

said film complying with the conditions of UL 94 and further exhibiting no surface  
cracking after 1000 hours weathering in accordance with ISO 4892 ;

wherein said film exhibits a longitudinal modulus of elasticity of greater than  
3200 N/mm<sup>2</sup> after said film has been heat treated for 100 hours at 100 °C and

Application No.: 09/760,169  
Filing Date: January 12, 2001  
Page: 6

said crystallizable thermoplastic ~~is selected from the group consisting~~ consists of polyethylene terephthalate, or polybutylene terephthalate or mixtures thereof.

22. (Previously Presented) A film according to Claim 21, said film further comprising hydrolysis stabilizer in said base layer alone.

23. (Previously Presented) A film according to Claim 1, wherein said film has a thickness of from 5 to 50  $\mu\text{m}$ .

24. (Canceled) Please cancel Claim 24.